

# SPECIFICATION

- Supplier : Samsung electro-mechanics
- Product : Multi-layer Ceramic Capacitor
- Samsung P/N : **CL21B225KAFNNNE**
- Description : **CAP, 2.2 $\mu$ F, 25V,  $\pm$ 10%, X7R, 0805**

## A. Samsung Part Number

CL   21   B   225   K   A   F   N   N   N   E  
①   ②   ③   ④   ⑤   ⑥   ⑦   ⑧   ⑨   ⑩   ⑪

<b>① Series</b>	Samsung Multi-layer Ceramic Capacitor									
<b>② Size</b>	0805 (inch code)	L: 2.0 $\pm$ 0.1	mm	W: 1.25 $\pm$ 0.1	mm					
<b>③ Dielectric</b>	X7R			<b>⑧ Inner electrode</b>	Ni					
<b>④ Capacitance</b>	2.2 $\mu$ F			<b>Termination</b>	Cu					
<b>⑤ Capacitance tolerance</b>	$\pm$ 10 %			<b>Plating</b>	Sn 100% (Pb Free)					
<b>⑥ Rated Voltage</b>	25 V			<b>⑨ Product</b>	Normal					
<b>⑦ Thickness</b>	1.25 $\pm$ 0.1	mm		<b>⑩ Special</b>	Reserved for future use					
				<b>⑪ Packaging</b>	Embossed Type, 7" reel					

## B. Samsung Reliability Test and Judgement condition

	Performance	Test condition
<b>Capacitance</b>	Within specified tolerance	1kHz $\pm$ 10%      1.0 $\pm$ 0.2Vrms
<b>Tan <math>\delta</math> (DF)</b>	0.1 max.	
<b>Insulation Resistance</b>	10,000Mohm or 100Mohm $\cdot\mu$ F Whichever is Smaller	Rated Voltage      60~120 sec.
<b>Appearance</b>	No abnormal exterior appearance	Microscope ( $\times$ 10)
<b>Withstanding Voltage</b>	No dielectric breakdown or mechanical breakdown	250% of the rated voltage
<b>Temperature Characterisitcs</b>	X7R (From -55 $^{\circ}$ C to 125 $^{\circ}$ C, Capacitance change should be within $\pm$ 15%)	
<b>Adhesive Strength of Termination</b>	No peeling shall be occur on the terminal electrode	500g-F, for 10 $\pm$ 1 sec.
<b>Bending Strength</b>	Capacitance change :    within $\pm$ 12.5%	Bending to the limit (1mm) with 1.0mm/sec.
<b>Solderability</b>	More than 75% of terminal surface is to be soldered newly	SnAg3.0Cu0.5 solder 245 $\pm$ 5 $^{\circ}$ C, 3 $\pm$ 0.3sec. (preheating : 80~120 $^{\circ}$ C for 10~30sec.)
<b>Resistance to Soldering heat</b>	Capacitance change :    within $\pm$ 7.5% Tan $\delta$ , IR : initial spec.	Solder pot : 270 $\pm$ 5 $^{\circ}$ C, 10 $\pm$ 1sec.

	<b>Performance</b>	<b>Test condition</b>
<b>Vibration Test</b>	Capacitance change : within $\pm 5\%$ Tan $\delta$ , IR : initial spec.	Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours $\times$ 3 direction (x, y, z)
<b>Moisture Resistance</b>	Capacitance change : within $\pm 12.5\%$ Tan $\delta$ : 0.125 max IR : 12.5M $\Omega \cdot \mu F$ or Over	With rated voltage 40 $\pm 2$ °C, 90~95%RH, 500+12/-0hrs
<b>High Temperature Resistance</b>	Capacitance change : within $\pm 12.5\%$ Tan $\delta$ : 0.125 max IR : 25M $\Omega \cdot \mu F$ or Over	With 150% of the rated voltage Max. operating temperature  1000+48/-0hrs
<b>Temperature Cycling</b>	Capacitance change : within $\pm 7.5\%$ Tan $\delta$ , IR : initial spec.	1 cycle condition Min. operating temperature $\rightarrow$ 25°C $\rightarrow$ Max. operating temperature $\rightarrow$ 25°C  5 cycle test

**C. Recommended Soldering method :**

Reflow ( Reflow Peak Temperature : 260+0/-5°C, 10sec. Max )

\* For the more detail Specification, Please refer to the Samsung MLCC catalogue.